## Zortrax Resin DENTAL Model

Precise dental resin with a gypsum-like texture. Offers very low shrinkage and high level of detail sufficient for accurate modeling of teeth. Not meant for intraoral use.

Mechanical Properties	Metric	Imperial	Test Method
Tensile Strength	9.87 MPa	1430 psi	DIN EN ISO 527-1
Elongation at Break	6.1%	6.1%	DIN EN ISO 527-1
E-Modulus	0.175 MPa	25.4 ksi	DIN EN ISO 527-1
Other Properties	Metric	Imperial	Test Method
Other Properties Viscosity	Metric 33 - 57 mPa·s	<b>Imperial</b> 0.000689 - 0.00119 lbf·s/ft <sup>2</sup>	Test Method DIN EN ISO 2431
·		· ·	

Compatible with	Layer Thickness Range		Available Colors
ZORTRAX Inkspire	0.025 mm	0.000984 in	
	0.05 mm	0.00197 in	beige
	0.10 mm	0.00394 in	

The data presented in this document are intended for information and comparison purposes only. They should not be used for project specifications or its quality evaluation. The material's actual properties depend on the printing process conditions, the design structure and its purpose, test conditions, etc.

Product specifications are subject to change without notice.

Each user is responsible for complying with product safety standards, its intended use as well as the law and waste disposal (and recycling) rules for electrical and electronic equipment. Zortrax does not make any express or implied warranties, including but not limited to implied warranties of merchantability or fitness for a particular purpose.